## Reactive Dedoping Method for Non-Power-Driven Polymeric Schottky Junction Photodiode

<u>강민균</u>, 윤성원, 김주희, 정대성<sup>†</sup> 대구경북과학기술원(DGIST) (dchung@dgist.ac.kr<sup>†</sup>)

A simple and strategic junction engineering technology is reported to enhance non-power-driven polymeric Schottky junction photodiode performances by synergetic contributions of reactive dedoping effects. It is shown that dedoping poly(3-hexylthiophene-2,5-diyl) (P3HT) films with 1-propylamine (PA) solution meaningfully decreases not only defect-acceptor density but also intrinsic doping level, resulting in significantly enlarged depletion region width of metal-polymer Schottky junctions. Also, it is shown that non-solvent effects of PA-dedoping process further make paracrystalline disorder lower and thus, charge carrier mobility higher. As a result of such synergetic merits of the PA-dedoping method, non-power-driven green-selective polymeric Schottky junction photodiodes are reported with a high specific detectivity over  $6\times10^{12}$  Jones, low noise-equivalent power of  $5.05\times10^{-14}$  W Hz<sup>-0.5</sup>, fast temporal response of  $26.9~\mu$ s, and wide linear dynamic range of 201~dB.